



# Wunder-Mold

*Creating Quality Standards for the Industry*

**Ceramic Injection Molding**

**Precision Injection Molding**

---

## **Acetal Copolymer**

### Physical Properties

Specific Gravity	-	1.41 g/cc
Tensile Modulus	-	406000 psi
Tensile Strength (Yield)	-	8800 psi
Tensile Stress (Yield)	-	9720 psi
Tensile Strength (Break)	-	9860 psi
Flexural Modulus	-	375000 psi
Charpy Notched Impact Str.	-	2.5 ft-lb/in <sup>2</sup>
Notched Izod Impact (@73F)	-	1.0 ft-lb/in

These numbers are typical values for the properties listed. Depending on the end shape and environment, these values may be slightly different. Any questions and or for recommendations on how to design your Plastic Injection Molded Parts, please contact our Design Engineers at Wunder Mold

790 Eubanks Dr. ~ Vacaville, CA 95688 ~ Tel. (707)448-2349 Fax(707)448-6045

Email: [sales@wundermold.com](mailto:sales@wundermold.com)

Website: [WWW.WUNDERMOLD.COM](http://WWW.WUNDERMOLD.COM)