



Wunder-Mold 790 Eubanks Drive . Vacaville, California 95688 USA
Tel 707-448-2349 . Fax 707-448-6045 . www.wundermold.com
CREATING QUALITY STANDARDS FOR THE INDUSTRY

Ceramic Injection Molding

Precision Injection Molding

WM-995-AI 99.5% Aluminum Oxide Ceramic

WM-995-AI is a 99.5% pure Aluminum Oxide Ceramic. It has adequate strength coupled with excellent hardness and wear resistance. Components which would typically use WM-995-AI include but are not limited to are: Fluid Metering, Semiconductor Tooling Components, Medical Components, Wear resistant parts, Aerospace Applications and Food and Beverage Applications.

Physical Properties

Color	-	White-Ivory
Sintered Density	-	≥3.90 g/cc
Bending Strength	-	400 MPa
Compressive Strength	-	2000 MPa
Fracture Toughness (NB)	-	4.0 MPa ^½
Hardness	-	1900 (HV10)
Thermal Conductivity	-	30 W/m*K

Chemical Properties

Al ₂ O ₃	-	≥ 99.5 wt%
MgO	-	≤ 0.12 wt%
Na ₂ O	-	≤ 0.10 wt%
SiO ₂	-	≤ 0.07 wt%
CaO	-	< 0.03 wt%

These numbers are typical values for the properties listed. Depending on the end shape and environment, these values may be slightly different. Any questions and or for recommendations on how to design your Ceramic Injection Molded Parts, please contact our Design Engineers at Wunder Mold.

Email: sales@wundermold.com